

## CC Quantum<sup>®</sup> CI

### Crack Injection Resin

#### CHARACTERISTICS

CC Quantum CI crack injection adhesive is a two part epoxy resin adhesive with low viscosity and high penetrating properties. CC Quantum CI is used for repairing cracks in concrete, masonry and wood.

The system has been developed to offer fast injection application and has excellent surface wetting.

CC Quantum CI has been specially developed to bond to both dry and damp surfaces.

#### APPLICATIONS

- Structural crack repair
- Low pressure injection of cracks in structural concrete, masonry, wood, etc
- Structural injection & grouting repairs

#### BENEFITS

- Conforms well with substrate damage, holes, dents or similar
- Solventless
- Excellent long-term performance
- Good physical performance after curing, strong toughness
- Water and Corrosion resistant
- Low viscosity aids penetration
- Good chemical resistance
- Excellent bonding compatibility with CC Quantum A and CC Quantum S

#### STANDARDS

- ASTM

## DESCRIPTION

### Form

Component	Texture	Colour
Part A: - Epoxy	Paste	Grey
Part B: - Hardener	Paste	White
Part A+B mixed	Paste	Light Grey

### Technical Data

Mixing ratio (A: B)	2:1
Density	1.1kg/litre
Service Temperature	5-40°C
Pot life (in minutes)	60 min at 25°C
Setting time	1-2 hrs. at 25°C
Cure Time	18 hours at 25°C

### Mechanical Properties

PROPERTY	TEST METHOD	TYPICAL VALUE	UNITS
Tensile Strength*	ASTM D638	60	MPa
Flexural Strength*	ASTM D790	95	MPa
Compressive Strength*	ASTM D695	105	MPa
Compressive Modulus*	ASTM D695	1.4	GPa
Adhesion to Concrete	ASTM D4541	2.7	MPa

\* Tested at 7 days at 20°C.

NOTE: All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## INSTRUCTIONS

### Substrate Preparation

Prior to application of any CC Quantum material products it is expected that the substrate be appropriately prepared according to the following:

- Ensure that all surfaces are cleaned, this entails the removal of a surface contaminates such as oils, grease, dust and other contaminates which could affect the bonding of the CC Quantum system.
- Abrasive cleaning and routing methods are recommended. Use clean, oil-free compressed air to remove dust or debris
- Specifically, for Concrete, Mortar and Stone which is still in good working condition, it is recommended to Mechanically abrade the surface with a needle gun, water blast, grit blast or grind. For small areas wire brushing (mechanical) is adequate.
- For degraded substrates, it is recommended to remove the affected area and restore allowing sufficient time to cure before applying CC Quantum System.

### Mixing

Part A: part B = 2: 1 by weight

Thoroughly stir both components Part A (Epoxy) and Part B (Hardener) separately using a slow running stirrer with a helical paste mixer or by hand if dealing with small quantities until a uniform colour is reached.

### Application

- CC Quantum L shall be applied using trowel, spatula or other similar equipment which will allow for an even and smooth application.
- The adhesive shall be applied to ensure an even flat surface
- CC Quantum L shall be allowed to dry prior to additional working

### Cleaning

Cleaning of applicator tools and surrounding surfaces can be achieved using an appropriate solvent (MEK or Acetone). Once the Adhesive has cured, the only means of removal shall be mechanically.

### Important Notes

- For simplicity and accuracy related to curing times and strength, always mix a full adhesive kit.
- Avoid part mixture to ensure correct ratio of Resin and Hardener
- Always take note of pot life, ensure CC Quantum L can be completely applied within the given time for the working temperature.
- Avoid diluting the mixture as this will affect curing time and bonding strength.
- During mixing, ensure there are no trapped air bubbles as will affect curing time and bonding strength.
- Ensure there is no standing water or other liquids on the application surface.
- An increased curing temperature can accelerate curing time, refer to technical data above.

For further information, consult our Technical Experts.

### Handling Precautions

- Use appropriate Personal Protective Equipment (PPE) when handling CC Quantum L mixture.
- At all times, avoid contact with the eyes and direct skin
- If mixture contacts eyes, immediately consult proceed to first aid to commence washing eye with water or specific eye bath liquid for up to 15 minutes. After which consult a doctor.
- If skin contact occurs, proceed to first aid and wash skin thoroughly.
- If mixture is swallowed, it is not recommended to induce vomiting. Rather proceed to first aid to receive medical attention.

For more information refer to Material Safety Data Sheet.

## SIGNBOARD

The contents shall be clearly marked on the product package:

- a) Manufacturer and address.
- b) Product name, brand and standards.
- c) Date of manufacture and batch number.
- d) Product quantity.
- e) Attention.

## PACKAGING

Available in 2 & 20 Litre packs

## TRANSPORT AND STORAGE

Store in dry conditions, storage temperatures should not drop below  $-5^{\circ}\text{C}$  or exceed  $40^{\circ}\text{C}$ , avoid direct sunlight and fire. Handle with care.

## SHELF LIFE

When stored at room temperature ( $25^{\circ}\text{C}$ ), the shelf life will be at least 12 months from the date of manufacture.

## AUSTRALIA

1/196 Mahoneys Road  
Thomastown. Victoria  
AUSTRALIA  
3074

Email: [enquiries@cathaycomposites.com.au](mailto:enquiries@cathaycomposites.com.au)

Web: [www.cathaycomposites.com](http://www.cathaycomposites.com)

ABN: 88 629 716 927

### Important notice

The data and information provided in this datasheet represent the typical properties that can be obtained from these products when properly processed in a controlled environment. The user should make their own assessment of the suitability of these products for the purpose required by conducting appropriate testing under conditions as close as possible to the proposed manufacturing conditions. Any advice or recommendation is given in good faith and no further duty or responsibility is accepted by the company. All such advice and every sale is subject to Cathay Composite's standard terms and conditions. The company reserves the right to change specifications without notice and customers should satisfy themselves that they are using the current version of the Technical Data Sheet.